









Alterfil K Technical Data

label no./ yarn count	available make-ups	fields of application	recommended needle size Nm	tensile strength cN	stretch %	shrinkage %	fastness to washing according to DIN EN ISO 105-C06	rub resistance according to DIN EN ISO 105-X12	lightfast according to DIN EN ISO 105-B01/02	fastness to perspiration according to DIN EN ISO 105-E04
Alterfil K 150 107 dtex x 2	2.500 m 	men's and boy's outerwear, women's outerwear, children's outerwear, sewing on buttons	60 - 70	990	17,0 - 19,0	< 1	4	4	5 - 6	4 - 5
Alterfil K 120 132 dtex x 2	2.500 m 	men's and boy's outerwear, women's outerwear, children's outerwear, sewing on buttons	70 - 80	1150	18,0 - 20,0	< 1	4	4	5 - 6	4 - 5
Alterfil K 80 215 dtex x 2	2.500 m 	men's and boy's outerwear, women's outerwear, children's outerwear, sewing on buttons	90-120	2080	18,5 - 20,5	< 1	4	4	5 - 6	4 - 5
Alterfil K 50 215 dtex x 3	2.500 m 	men's and boy's outerwear, women's outerwear, children's outerwear, sewing on buttons	90 - 130	3050	20,0 - 22,0	< 1	4	4	5 - 6	4 - 5
Care		    								



QM-System zertifiziert
DIN EN ISO 9001:2008



Alterfil Nähfaden GmbH

Bahnhofstraße 33 · D-09569 Oederan · phone +49 (3 72 92) 26 112-115 · alterfil@alterfil.de
www.alterfil.de