

# Alterfil L (400, 200, 180) Technical Data

label no./ yarn count	available make-ups	fields of application	recommended needle size Nm	tensile strength cN	stretch %	shrinkage %	fastness to washing according to DIN EN ISO 105-C06	rub resistance according to DIN EN ISO 105-X12	lightfast according to DIN EN ISO 105-B01/02	fastness to perspiration according to DIN EN ISO 105-E04	
<b>Alterfil L 400</b> 33 dtex x 2	5.000 m 20.000 m	for hardly visible blind stitch seams in the high-quality and extra-fine application field	55 - 65	420	15,0 - 17,0	< 1	4	4	5 - 6	4 - 5	
<b>Alterfil L 200</b> 50 dtex x 2	5.000 m 20.000 m	filigree serging and high-quality blind stitch works	60 - 70	650	15,5 - 18,0	< 1	4	4	5 - 6	4 - 5	
<b>Alterfil L 180</b> 78 dtex x 2	5.000 m 20.000 m	edge protection and fine serging seams, invisible and blind stitch works; fine upper and underthread on multi-needle machines	65 - 80	980	16,5 - 18,5	< 1	4	4	5 - 6	4 - 5	
<b>Care</b>											



QM-System zertifiziert  
DIN EN ISO 9001:2008

**Alterfil Nähfaden GmbH**

Bahnhofstraße 33 · D-09569 Oederan · phone +49 (3 72 92) 26 112-115 · alterfil@alterfil.de  
www.alterfil.de