

Alterfil T Technical Data

label no./ yarn count	available make-ups	fields of application	recommended needle size Nm	tensile strength cN	stretch %	shrinkage %	fastness to washing according to DIN EN ISO 105-C06	rub resistance according to DIN EN ISO 105-X12	lightfast according to DIN EN ISO 105-B01/02	fastness to perspiration according to DIN EN ISO 105-E04	
Alterfil T 120 140 dtex x 1	5.000 m 10.000 m	knitted fabrics, swimwear, underwear, bodice	60-80	500	28,0 - 31,0	< 1	4	4	5 - 6	4 - 5	
Alterfil T 120 185 dtex x 1	5.000 m 10.000 m	knitted fabrics, swimwear, underwear, bodice	70-80	650	28,0 - 31,0	< 1	4	4	5 - 6	4 - 5	
Care											

Alterfil B Technical Data

label no./ yarn count	available make-ups	fields of application	recommended needle size Nm	tensile strength cN	stretch %	shrinkage %	rub resistance according to DIN EN ISO 105-X12	rub resistance according to DIN EN ISO 105-X12	lightfast according to DIN EN ISO 105-B01/02	fastness to perspiration according to DIN EN ISO 105-E04	
Alterfil B 250 125 dtex x 1	5.000 m 10.000 m	serging of very fine and light fabrics for men´s and boy´s outerwear, women´s outerwear and underwear	55-80	460	24,5 - 27,5	< 1	4	4	5 - 6	4 - 5	
Alterfil B 120 185 dtex x 1	5.000 m 10.000 m 25.000 m)*	women´s outerwear, men´s and boy´s outerwear, sportswear, swimwear, universal application overedge, covering and coverlock seams, flatlock seams, looper thread for multi-needle machines	65 - 90	630	27,0 - 30,0	< 1	4	4	5 - 6	4 - 5	
Alterfil B 100 185 dtex x 2	5.000 m 10.000 m)*	women´s outerwear, men´s and boy´s outerwear, sportswear, swimwear, universal application overedge, covering and coverlock seams, flatlock seams, looper thread for multi-needle machines	80 - 110	1270	27,5 - 30,5	< 1	4	4	5 - 6	4 - 5	
)* available in colour upon request									
Care											



QM-System zertifiziert
DIN EN ISO 9001:2008

Alterfil Nähfaden GmbH

Bahnhofstraße 33 · D-09569 Oederan · phone +49 (3 72 92) 26 112-115 · alterfil@alterfil.de
www.alterfil.de