







Alterfil Elastic Technical Data

label no./ yarn count	available make-ups	fields of application	recommended needle size Nm	tensile strength cN	stretch %	shrinkage %	fastness to washing according to DIN EN ISO 105-C06	rub resistance according to DIN EN ISO 105-X12	lightfast according to DIN EN ISO 105-B01/02	fastness to perspiration according to DIN EN ISO 105-E04	
Alterfil Elastic no. 120 115dtex x 3	3.000 m 	for the processing of stretch materials in the field of sportswear, underwear and swimwear, quilting stitch seams with high elasticity	65 - 90	890	55,0 - 62,0	< 1	4	4	5 - 6	4 - 5	
Care		    									



QM-System zertifiziert
DIN EN ISO 9001:2008

Alterfil Nähfaden GmbH